PALM LABS ADHESIVES

3063 Enterprise Road, DeBary FL, 32713 Phone (321) 710-4850 Fax (321) 710-4875

Email: Sales@PalmLabsAdhesives.com

TURBO SEAL - SERIES 52 RED HIGH TEMPERATURE GASKET ELIMINATOR FLANGE SEALANT

TURBO SEAL SERIES 52 is an anaerobic gasket sealant, which develops medium strength in a short time. The compound cures in the absence of air between close fitting surfaces. Provides resistance to low pressure immediately after assembly of flanges.

Part Numbers for this TDS: 52-050, 52-300

Applications:

- Typically used as a form-in-place rigid flange connections in high temperature applications.
- Excellent chemical resistance.
- Typical uses are engine casing and gearboxes.
- Thixotropic nature reduces the migration of liquid product after application.

ADHESIVE PROPERTIES

Composition	Dimethacrylate ester	
Appearance	Red	
Viscosity cP	188,000 – 500,000 cps Thixotropic	
-	(Brookfield RVT @ 25°C Spindle 7 @ 20 rmp)	
Specific Gravity	1.10	
Flash Point	>93°C	
Solvent Content	None	

CURING PROPERTIES

Handling Cure Time – Unprimed Surfaces	2 – 8 Hours	
Handling Cure Time – Primed Surfaces	30 Minutes - 4 Hours	
	2	
Compressive Shear Strength	> 7.5 N/mm ² > 1,085 psi	
	(ISO 10123 >24 hours @ 22°C Steel Pins & Collars)	
Lap Shear Strength	5 N/mm ² 725 psi	
	(ISO 4587 Steel - grit based)	
Tensile Strength	7.5 N/mm ² 1085 psi	
	(ISO 6922 Steel - grit based)	
Temperature Range	-65 to 400°F	

PHYSICAL PROPERTIES

Coefficient of Thermal Expansion	$80x10^{-6}$	ASTM D 696, K-1
Coefficient of Thermal Conductivity	0.10	ASTM C 177 W/(m.K)
Specific Heat	0.30	kJ/(kg.K)

CHEMICAL RESISTANCE

		% Initial Strength	Retained
Chemical	<u>Temperature</u>	<u>500 Hours</u>	<u>1000 Hours</u>
Acetone	$22^{\circ}\mathrm{C}$	100	95
Ethanol	22°C	90	85
Motor Oil	125°C	100	100
Gasoline	$22^{\circ}\mathrm{C}$	75	75
Brake Fluid	$22^{\circ}\mathrm{C}$	95	95
Water/Glycol	87°C	110	110

Directions for Use:

- For best results, clean all surfaces (external and internal) with a cleaning solvent and allow the solvent to
- Apply manually as a continuous bead or by screen-painting to one of surface flanges.

 Low pressure can be used when testing to confirm a complete seal immediately after assembly.

- Flanges should be tightened as soon as possible after assembly to avoid shimming.

Storage:

Anaerobic adhesives are ideally stored in a cool, dry place in unopened containers at room temperature, 46°F to 86°F. Do not return unused material to its original container.

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the Warranty: All products purchased from or supplied by Palm Labs Adhesives are subject to terms and conditions set out in the contract. Palm Labs Adhesives warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Palm Labs Adhesives is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Palm Labs Adhesives makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will nor infringe any patent.

Palm Labs Adhesives

Toll Free Phone 1-855-752-4583 Fax (321) 710-4875 Email: Sales@PalmLabsAdhesives.com 02/06/2017